



- 材 質……SUJ-2 (高炭素クローム軸受鋼)
- 表面硬度……60HRC以上
- 表面粗度……HGS6~HGS50 0.2a(Ra)
 HGS60,80,100 0.4a(Ra)

- 内は標準在庫品です。
- 内は準標準品です。
- 内は受注製作品です。

呼び形番	呼び径 D (mm)	外径許容差 (μm) g6	規 格 L								長 さ (mm)						呼び径 D (mm)	有効硬化層 深さ (mm)	重 量 W (kgf/m)	
			100	200	300	400	500	600	800	1000	1200	1500	2000	2500	3000					
HGS 6	6	-4~-12															6	0.5以上	0.23	
HGS 8	8	-5~-14															8		0.40	
HGS 10	10		-6~-17															10	0.8以上	0.62
HGS 12	12																12	0.89		
HGS 13	13																	13	1.0以上	1.04
HGS 16	16																	16		1.58
HGS 20	20	-7~-20															20	2.47		
HGS 25	25																25	3.85		
HGS 30	30																	30	5.55	
HGS 35	35	-9~-25															35	7.55		
HGS 40	40																40	9.87		
HGS 50	50																	50	15.40	
HGS 60	60	-10~-29															60	1.5以上	22.20	
HGS 80	80																80		39.50	
HGS 100	100		-12~-34																100	61.65

HGS2から対応できます。
HGS2~5 有効硬化層深さ0.5mm以上